

# Additional information Acoustic materials

## AC10-400F

Noise absorption coefficient [ $\alpha$ ] Octave	
Article	AC10-400F/1.45X60
Weight	400 g/m <sup>2</sup>
Thickness	10 mm
125	0,20
250	0,55
500x	0,75
1000	0,65
2000	0,80
4000	0,75
$\alpha$	0,75
NRC	0,70
Sound absorbing cat.	C

### Tested Configuration

- Tested with a 200 mm distance to the floor with a frame edges closed
- 1-side reference surface
- Volume of testing room is 200 m<sup>3</sup>
- Tested surface 12 m<sup>2</sup>

**The information stated is indicative  
and may vary depending on the application**